

**APPENDIX II**  
**EXPLANATORY DRAWINGS**


**BEST AVAILABLE COPY**

1/3

## MECHANISM OF CATALYST SUPPORTING OF PRESENT INVENTION (1)

### 1) Lattice Defects by Element Substitution

• Formation of lattice defects within cordierite crystal





2/3


## MECHANISM OF CATALYST SUPPORTING OF PRESENT INVENTION (2)

### 2) Fine Cracks

• Formation of Cracks (fine cracks) in glass phase




Giving thermal shock provides thermal stress due to difference in thermal expansion coefficient between amorphous and crystal phases, to form fine cracks, having a size in a range of 0.1-100nm



If a catalyst component is supported on a cordierite having fine cracks, catalyst ions are supported on fine cracks, which are fired to form a catalyst metal

3/3

## MECHANISM OF CATALYST SUPPORTING OF PRIOR ART




Normal cordierite has a crystal structure as shown in the left figure and does not have points to support a catalyst component



The left figure shows the surface of cell wall of a monolith support body, having a smooth surface for the catalyst component, so that there are no points to support a catalyst

↓ Catalyzed



By forming a  $\gamma$ -alumina layer having a large specific surface area on the surface of cordierite, a catalyst component is supported on the  $\gamma$ -alumina layer

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☒ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**